



Benefits

- Thermal conductivity 1.1 W/m-K, 3x FR4
- Thermal impedance 0.15° C-in²/W (0.97° C-m²/W)
- Available as laminate only
- Economical
- High dielectric strength
- High reliability
- Available worldwide

Thermal Clad Metal Core PCB's (MCPCB's) minimize thermal impedance and conduct heat more effectively than standard printed wiring boards (PWB's). These substrates are more mechanically robust than thick-film ceramic and direct bond copper construction.

Thermal Clad is a cost-effective solution which can eliminate components, allow for simplified designs, smaller devices and an overall less complicated production process. Additional benefits of Thermal Clad include lower operating temperatures, resulting in longer component life and increased durability.

The technology of Thermal Clad resides in the dielectric. This datasheet highlights the performance characteristics of Thermal Clad HR T30.20, with twenty plus year's industry proven dielectric for a multitude of applications including LED, Power Conversion, Heat-Rails, Solid State Relays and Motor Drives.

For Additional Info (800) 347-4572
www.bergquistcompany.com



HR T30.20 Dielectric Typical Values

HRT T30.20	VALUE	TEST METHOD
THERMAL PROPERTIES		
Thermal Conductivity	1.1 W/m-K	ASTM D5470
Thermal Resistance	0.15°C-in ² /W (0.97°C-cm ² /W)	ASTM D5470
Thermal Impedance	0.90°C/W	BG-RD2018
Glass Transition	90°C	ASTM E1356
ELECTRICAL PROPERTIES		
Dielectric Constant	7	ASTM D150
Dissipation Factor	0.005 (@12Hz)	ASTM D150
Capacitance	450 pF/in ² (70pF/cm ²)	ASTM D150
Volume Resistivity	10 ¹⁵ Ω-m	ASTM D5109
Surface Resistivity	10 ¹⁴ Ω/sq	ASTM D5109
Dielectric Strength	2200 V/mil (85 kV/mm)	ASTM D149
Breakdown Voltage	7.5 kVAC	ASTM D149
MECHANICAL PROPERTIES		
Color	Light Green	Visual
Dielectric Thickness	0.003" (76 μm)	Visual
Peel Strength@25C	9 lb/in (1.6 N/mm)	ASTM D2561
CTE in X/Y/Z Axis <T _g	25 μm/m°C	ASTM D1861
CTE in X/Y/Z Axis >T _g	95 μm/m°C	ASTM D1861
Storage Modulus	14/0.3 GPa (@25°C/150°C)	ASTM 4065
CHEMICAL PROPERTIES		
Water Vapor Retention	0.13% wt.	ASTM E595
Out-Gassing Total Mass Loss	0.31% wt.	ASTM E595
Collect Volatile Condensable Material	< 0.01% wt.	ASTM E595
AGENCY RATINGS & DURABILITY		
U.L. Continuous Operating Temperature	150°C	U.L. 746B
U.L. Flammability	V-0	U.L. 94
Comparative Tracking Index (CTI)	600V	U.L. 746A/IEC60112
Solder Float	Pass	IPC TM 650 2.4.13

Please test this material in your application. Bergquist provides this engineering data for design guidance only. Depending on your application, the observed material performance may vary.

Applications

- High Power LED applications
- Power conversion
- Heat-rails
- Solid state relays
- Motor drives
- LED applications

Configurations Available†:

- Standard available panel sizes:
 - 20" x 24" (508mm x 610mm)
Usable area: 19" x 23"
(483mm x 584mm)
 - 18" x 24" (457mm x 610mm)
Usable area: 17" x 23"
(432mm x 584mm)
 - 18" x 25" (457mm x 635mm)
Usable area: 17" x 24"
(432mm x 610mm)

Standard Panel Options‡

- 040AL 5052 x HR T30.20 x 1 oz
- 040AL 5052 x HR T30.20 x 2 oz
- 062AL 5052 x HR T30.20 x 1 oz
- 062AL 5052 x HR T30.20 x 2 oz

†For any non-standard configuration or panel please contact the Thermal Clad Factory Sales Department at (800) 950-7956.



www.bergquistcompany.com

The Bergquist Company -
North American Headquarters
Phone: 800-347-4572
Fax: 952-835-4156

The Bergquist Company -
European Headquarters
Phone: 31-35-5380684
Fax: 31-35-5380295

The Bergquist Company -
Asian Headquarters
Phone: 852-2690-9296
Fax: 852-2690-3408

All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKETABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE A PRODUCT. No statement, purchase, order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer.

PDS_HRT3020_1212